



**Betu Group Pty Ltd**  
Unit 17 / 14 Loyalty Road, North Rocks, NSW 2151  
Email: sales2betu@gmail.com  
Phone: 0470 268 112  
Website: www.betu.com.au

**B E T U**

# DATA SHEET

## EPOXY PUTTY

### 2 PACK, CRACK REPAIR KIT

#### DESCRIPTION

Betu Epoxy Putty is a two part construction strength repair paste for concrete. It is extremely high strength, fast curing, and easy to apply after mixing. Ideal for filling and repairing holes, cracks, and damage to concrete surfaces. Betu Epoxy Putty is low VOC and is resistant to a wide variety of chemicals. Suitable for use in preparation for the application of most Betu systems.

#### PRODUCT INFORMATION

<b>Pot Life</b>	30 minutes after mixing.
<b>Shelf Life</b>	2 years. Store in a cool, dry area and out of direct sunlight
<b>Mixing</b>	(1:1) 1 Parts (Part A): 1 Part (Part B)
<b>Coverage</b>	Highly Variable
<b>Clean Up</b>	Clean tools with Betu Epoxy Thinners while still wet
<b>Recoat Time</b>	1 hour or once firm
<b>Return to Service</b>	Initial hardness: 1 hour Full chemical cure: 7 Days at 25°C
<b>Colour</b>	Grey, when mixed (may yellow or darken when exposed to sunlight)

#### RECOMMENDED USES

- Concrete columns and pre-cast concrete
- Crack repair
- Patching and joint filling
- Grouting bolts
- Bonding compressed cement sheets
- Concrete pipes and tanks
- Flush-filling countersunk screws in Fibre cement sheets
- Structural repairs

#### FEATURES & BENEFITS

- Excellent chemical resistance
- Excellent adhesion
- High build application
- Extreme impact resistance
- Low VOC
- Kit Size: 2L, 4L
- Extreme bond strength

#### ENVIRONMENTAL CONDITIONS

Temperature and the surrounding atmospheric conditions will play a part in the curing process. Attention also needs to be paid to the substrate temperature which should be NO LESS than 5°C.

Industry standards recommend the accurate recording of times and dates, batch numbers, consumption rates, and environmental conditions including the substrate and air temperatures, humidity levels, and dew point readings during both the application and curing process. Full material warranties cannot be provided unless all the relevant data has been recorded accurately.

#### SURFACE PREPARATION

Ensure the concrete is sufficiently cured to the recommended minimum of 28 days from completion. Diamond grind or Polyvac the substrate. The surfaces must be clean, dry, and free from all traces of loose material, old coatings, curing compounds, release agents, laitance, oil, and grease, etc. This must be completed by diamond grinding or a suitable cleaning method. To check that all traces of oil and other contaminants have been completely removed, sprinkle a few drops of water over the surface. If all water is quickly absorbed, the surface is sufficiently oil and grease-free. If water forms into globules that remain on the surface, further thorough treatment of the substrate is necessary. Substrate compression strength should be at least 25MPa, cohesive bond strength at least 1.5MPa, and moisture content below 4%. Repair and fill cracks with Betu Epoxy Putty or Concrete Repair Kit.



Betu Group Pty Ltd  
Unit 17 / 14 Loyalty Road, North Rocks, NSW 2151  
Email: sales2betu@gmail.com  
Phone: 0470 268 112  
Website: www.betu.com.au

**B E T U**

# DATA SHEET

## EPOXY PUTTY

### 2 PACK, CRACK REPAIR KIT

#### PRODUCT APPLICATION

Thoroughly mix (1:1) 1 Part A Epoxy Putty with 1 Part B Epoxy Putty Hardener (1:1) on a smooth surface with a spatula. No induction time is required and repairs can begin immediately. Spatula or trowel mixed putty mixture into clean cracks, joints, divots or other areas needing repair. Grind surface flat and level before coating to ensure a desirable appearance.

#### MIXING

- Mix Part A and Part B individually prior to combining.
- Combine 1 Part A and 1 Part B by volume.
- Part A is white in colour, compared to Part B which is a dark grey.
- Thoroughly mix until a light grey is formed. Inaccuracies and poor mixing will result in lower physical properties of the cured system. If the error is great enough, the system may not cure to satisfaction.

#### CAUTIONS

- Do not use the same mixing tool in both Part A and Part B as this will cross-contaminate the product.
- Cross contamination will cause lumps in the individual tins.

#### PHYSICAL PROPERTIES

<b>Rate of Burning</b>	ASTM D635: Self-Extinguishing
<b>Bond Strength to Concrete</b>	100% Concrete Failure
<b>Impact Strength</b>	75 MPa
<b>Minimum Application Temperature</b>	5°C

In an emergency, contact the Poisons Information Centre on 13 11 26 or a doctor for advice.

**IF THE SITUATION IS LIFE THREATENING, DIAL 000 IMMEDIATELY.**

DISCLAIMER: Please ensure you read the SDS & TDS thoroughly & carefully before the use or application of any Betu product.

These documents contain information in context to how you will apply the product, including if it is being used in conjunction with any other products or systems, and to what surface the product will be applied. Betu does not accept any liability either directly or indirectly for any losses that arise from the use or application of the product in accordance with any advice, specification & recommendation given by the companies' documentation or representatives at any point in time. Application, performance & safety data may change from time to time. It is the user and/or applicators' responsibility to ensure they have the latest copy of any documentation pertaining to their project.

Industry standards recommend the accurate recording of times and dates, batch numbers, consumption rates and environmental conditions including substrate and air temperatures, humidity levels and dew point readings during both the application and curing processes. Full material warranties cannot be provided unless all the relevant data has been recorded accurately.